

COHRlastic®

Silicone Reinforced Solid



Reference	Colour	Durometer Shore A	Burst Strength kPa	Elongation at Break %
3320	Red	70	5171	< 10
4032	Grey	81	5171	< 10
4050	Grey	75	5171	< 10
4420	Brown	75	4136	< 10
4444	Red	73	5515	< 10
4451	Black	75	5171	< 10
4480	Dark Grey	81	5171	< 10

Values shown are typical and should not be used for writing specification.
Please contact our Customer Service Department for more details regarding our products.

Application Advantages

- Dimensionally stable.
- Conformable.
- Low compression set.
- Detect-free smooth surface.
- Long cycle life in press pad applications.
- Low outgassing.

Saint-Gobain Performance Plastics S.A.

Avenue du Parc 18
4650 Chaineux (Belgium)
Tel: +32/87 32 20 11
Fax: +32/87 32 20 51
sgppl.chaineux@saint-gobain.com

www.foams.saint-gobain.eu

COHRlastic is a registered trademark.
©2010 Saint-Gobain Performance Plastics Corporation
AFF-1518Eur-PDF-0610

The data and details in this leaflet were correct and up-to-date at the time of printing and are intended to provide information on our products and their possible applications. It is the user's responsibility to make sure he is in possession of the latest version of the product data sheet. This leaflet is not a specification and does not assure specific product characteristics or make reference to the suitability of the products for a definite application. Because Saint-Gobain cannot anticipate or control every application, we strongly recommend testing of this product under individual application conditions. The application, the use and the conversion of this product are under the user's responsibility.