

## PRODUCT DESCRIPTION

COHRLastic® CF 3320 a thin flexible abrasion resistant reinforced general purpose silicone rubber. This product is often used as belting, gasketing and press pads. CF 3320 offers an asbestos free gasketing that will function through a wide temperature range. **CF3320 HAS PROVEN SUCCESSFUL AS A GENERAL PURPOSE FLEX OPERATION PRESS PAD.**

Physical Properties		Test Method
Thickness (mm)	1.6 2.4 3.2	ASTM D-751
Fiberglass (style)	1564	
Fiberglass Thickness (in)	0.36	ASTM D-751
Break Strength, Warp (ppi)	300	ASTM D-751
Elongation (%)	<10	ASTM D-751
Diaphragm Burst Strength (psi)	750	ASTM D-751
Weight by thickness (lbs/yd <sup>2</sup> )	1.6 = 4.1 2.4 = 5.9 3.2 = 7.8	ASTM D-575
Durometer with fabric (shore A)	1.6 = 74 2.4 = 66 3.2 = 65	ASTM D-2240
Durometer rubber compound (shore A)	50	ASTM D-2240
Weight Loss, 4 hours @ 250°F (%)	1.0	---
Temperature Range (°C)		-75 +260
Press Pad Temp. Limit (°C)		175
Colour		Red

All physical properties are typical values and should not be used for writing specifications.

## AVAILABILITY

Factory stock is available as 36" wide yard goods.

SAINT-GOBAIN Performance Plastics S.A.  
 Avenue du Parc 18  
 4650 CHAINEUX - BELGIUM  
 Phone : +32/87.32.20.11  
 Fax : +32/87.32.20.51  
 E-mail : [sgppl.chaineux@saint-gobain.com](mailto:sgppl.chaineux@saint-gobain.com)

The data and details in this leaflet were correct and up-to-date at the time of printing and are intended to provide information on our products and their possible applications. It is the user's responsibility to make sure he is in possession of the latest version of the product data sheet. This leaflet is not a specification and does not assure specific product characteristics or make reference to the suitability of the products for a definite application. Because Saint-Gobain cannot anticipate or control every application, we strongly recommend testing of this product under individual application conditions.

## FIBERGLASS REINFORCED SOLID

### APPLICATION ADVANTAGES

- Unlimited life at room temperature
- Silicone is odourless, dimensionally stable
- Formulated to meet AMS 3320 Rev. G specification
- Good conformability, lubricating oil resistant
- Excellent compression set resistance, smooth void free surface
- Balanced coating provides two working surfaces
- Approximate cycle life is 200