

COHRlastic®

Closed Cell Silicone Sponge



Product	Colour	Compression Deflection kPa	Tensile Strength kPa	Elongation at break %	Compression Set %
R10470M	Orange-Tan Black	70	620	1505	25
R10470F	Orange-Tan	110	900	200	25
R10480S	Red	35	345	75	5
R10480M	Brown	70	520	125	5
R10460M	Dark Blue	70	520	125	5
R10450M	Blue-Grey	104	860	<10	25
R10490M	Blue	104	1240	125	25
R10404F	Light Green	138	830	150	15
R10400	Grey	70	690	250	10

*Values shown are typical and should not be used for writing specification.
Please contact our Customer Service Department for more details regarding our products.*

Application Advantages

- Excellent sealing properties.
- Broad operating temperature range.
- Low outgassing.
- Low water absorption.
- Low compression set.
- Chemically inert.
- Excellent weatherability.
- Excellent release characteristics.
- Good chemical and fluid resistance.

Saint-Gobain Performance Plastics S.A.

Avenue du Parc 18
4650 Chaineux (Belgium)
Tel: +32/87 32 20 11
Fax: +32/87 32 20 51
sgppl.chaineux@saint-gobain.com

www.foams.saint-gobain.eu

COHRlastic is a registered trademark.
©2010 Saint-Gobain Performance Plastics Corporation
AFF-1517Eur-PDF-0610

The data and details in this leaflet were correct and up-to-date at the time of printing and are intended to provide information on our products and their possible applications. It is the user's responsibility to make sure he is in possession of the latest version of the product data sheet. This leaflet is not a specification and does not assure specific product characteristics or make reference to the suitability of the products for a definite application. Because Saint-Gobain cannot anticipate or control every application, we strongly recommend testing of this product under individual application conditions. The application, the use and the conversion of this product are under the user's responsibility.