

COHRLastic® Silicone Solid

COHRLastic® Silicone Solid General Properties

Product	Color	Durometer (Shore A)	Tensile Strength kPa	Elongation at Break %	Compression Set
300/9030	Red	30	5.5	500	15%
400/9040	Red	40	5.5	500	15%
500/9050	Red	50	4.8	350	15%
600/9060	Red	60	4.8	200	15%
700/9070	Red	70	4.8	160	15%
9235	Grey	30	7.9	800	30%
9255	Grey	50	8.3	600	30%
9275	Grey	70	8.3	350	30%
EC102	Black	60	—	200	20%

Values shown are typical and should not be used for writing specifications.
Please contact our Customer Service Department for more details regarding our products.

The data and details in this leaflet were correct and up-to-date at the time of printing and are intended to provide information on our products and their possible applications. It is the user's responsibility to make sure he is in possession of the latest version of the product data sheet. This leaflet is not a specification and does not assure specific product characteristics or make reference to the suitability of the products for a definite application. Because Saint-Gobain cannot anticipate or control every application, we strongly recommend testing of this product under individual application conditions. The application, the use and the conversion of this product are under the user's responsibility.

Application Advantages

- Smooth defect-free surface
- Low compression set
- Low outgassing
- Excellent release characteristics
- Long service life
- Good chemical and fluid resistance

Saint-Gobain Performance Plastics S.A.
Avenue du Parc 18
4650 Chaineux (Belgium)
Tel: +32/87 32 20 11
Fax: +32/87 32 20 51

www.foams.saint-gobain.eu

COHRLastic is a registered trademark.
©2010 Saint-Gobain Performance Plastics
AFF-1519E-PDF-0610